



Paae 1/2

# **Lubrigrease SEP 415**

GRS-6016

General manufacturing synthetic grease

## **CLASSIFICATION**

DIN 51502 KPHC1.5N-40 ISO 6743 ISO-L-XDDIB1.5

## PRODUCT DESCRIPTION

Lubrigrease SEP 415 is a lithium complex thickened lubricating grease based on a high viscous synthetic oil. The grease contains antioxidants, corrosion inhibitors and EP/AW additives based on bismuth technology.

The lithium complex soap, together with the synthetic base oil, makes the product suitable for applications at elevated temperatures, heavily loaded bearings and in wet and corrosive environments. The complex soap structure also gives the product a high degree of mechanical stability.

This enhances the performance and prolongs re-lubrication intervals. The specially developed bismuth additive package gives the grease a very high load carrying capacity and excellent wear protection.

Lubrigrease SEP 415 is a modern high performance synthetic product suitable for both industrial and automotive applications. The consistency of the lubricating grease makes it suitable for use in industrial centralised lubrication systems.

- Excellent at high temperatures
- Very good mechanical stability
- High load carrying capacity
- Very good corrosion protection

## **TYPICAL TECHNICAL DATA**

Thickener **Lithium Complex** Base oil Synthetic oil Colour Visual Yellowish **NLGI** Grade ASTM D217 1,5 >260°C Dropping point IP 396 Base oil viscosity at 40°C ISO 12058 460 mm<sup>2</sup>/s Base oil viscosity at 100°C ISO 12058 48 mm<sup>2</sup>/s 4-ball weld load DIN 51350:4 3200 N

Temperature range -40°C to +140°C Max +200°C

#### **Health and Safety**

Based on available information, this product is not expected to produce adverse effects on health when used for the intended application and the recommendations provided in the Material Safety Data Sheet (MSDS) are followed. MSDS's are available upon request through your sales contract office, or via the Internet. This product should not be used for purposes other than its intended use. If disposing of used product, take care to protect the environment. Lubrita check oil level design is trade mark of PMM Ltd. or one of it's subsidaries.





Page 2/2

#### **TYPICAL TECHNICAL DATA**

Mechanical stability	100 2427	Typical Value
Penetration 60 strokes	ISO 2137	290-320
Penetration 100.000 strokes	ISO 2137	+20
Shell roll stability 50h/80°C	ASTM D1831mod	+35
Test & Co.		
Corrosion protection		
SKF Emcor WWO distilled water	ISO 11007mod	0-0
SKF Emcor WWO salt water	ISO 11007mod	2-2
SKF Emcor acid solution	ISO 11007	0-0
Copper corrosion 24h/100°C	ASTM D4048	1b
Water stability		
Water resistance	DIN 51807/1	1-90
Oil Separation		
Separation 168h/40°C	IP 121	5%
Lubrication ability		
SKF R2F test A	SKF	Pass
SKF R2F test B at 140°C	SKF	Pass
Anti-wear properties		
4-ball wear scar (1h at 400N)	DIN 51350:5	0,7 mm
Others		
Approx. density at 20°C	IPPM-CS/03	0,90
11 I	<b>,</b>	-,-

#### **Health and Safety**

Based on available information, this product is not expected to produce adverse effects on health when used for the intended application and the recommendations provided in the Material Safety Data Sheet (MSDS) are followed. MSDS's are available upon request through your sales contract office, or via the Internet. This product should not be used for purposes other than its intended use. If disposing of used product, take care to protect the environment. Lubrita check oil level design is trade mark of PMM Ltd. or one of it's subsidaries.